

Borehole numbers	Ni wt%	Cu wt %	S wt %	Pt ppm	Pd ppm	Pt+Pd ppm
PGE-Cu-Ni sulfide deposits and manifestations						
Western Nittis						
MT-76	0.25	0.14	0.65	0.13	1.15	1.28
MT-76	0.48	0.40	1.86	0.40	3.20	3.60
MT-77	0.12	0.36	1.08	0.65	3.67	4.32
MT-78	0.14	0.08	0.38	0.11	0.77	0.88
MT-79	0.12	0.07	0.41	0.10	0.56	0.66
MT-80	0.18	0.08	0.50	0.08	0.77	0.85
MT-80	0.22	0.12	0.72	0.15	1.07	1.22
MT-80	0.17	0.07	0.32	0.16	0.84	1.00
MT-81	0.24	0.13	0.67	0.16	1.18	1.34
MT-81	0.20	0.13	0.51	0.17	0.95	1.12
MT-82	0.07	0.07	0.37	0.12	0.55	0.67